

Impact of π-conjugated self-assembled monolayer structure on their electrical properties

Lionel Patrone, Grégory Delafosse, Bruno Jousselme, Yu-Pu Lin, Younal Ksari, Mathieu Abel, Mathieu Koudia, Jean-Marc Themlin, Serge Palacin

▶ **To cite this version:**

Lionel Patrone, Grégory Delafosse, Bruno Jousselme, Yu-Pu Lin, Younal Ksari, et al.. Impact of π-conjugated self-assembled monolayer structure on their electrical properties. TNT2014, Oct 2014, Barcelona, Spain. cea-02362750

HAL Id: cea-02362750

https://cea.hal.science/cea-02362750

Submitted on 14 Nov 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Impact of π-conjugated self-assembled monolayer structure on their electrical properties

L. Patrone[1], G. Delafosse[1], B. Jousselme[2], Y.-P. Lin[2], Y. Ksari[1], M. Abel[1], M. Koudia[1], J.-M. Themlin[1] and S. Palacin[2]

lionel.patrone@im2np.fr

[1]CNRS, IM2NP UMR 7334, Aix-Marseille Université, Campus de St Jérôme 13397 Marseille cedex 20, & ISEN-Toulon, Maison des Technologies, Pl. G. Pompidou F-83000 Toulon, France
[2]Laboratory of Innovation in Surface Chemistry and Nanosciences (LICSEN), DSM/IRAMIS/NIMBE CEA Saclay, F-91191 Gif-sur-Yvette Cedex, France

Molecular memory cells are likely to be among the most basic and important components of future molecule-based electronic devices. [1]. For instance a possible architecture for resonant tunnelling diodes consists in a self-assembled monolayer (SAM) of sigma-pi-sigma (σ-π-σ) organic molecules composed of alkyl-chains (σ) acting as tunnel barriers while a central π-conjugated moiety acts as a potential well [2]. In this work, we focused on SAMs of specially synthesized new organic molecules based on donor terthiophene (3T) or acceptor naphthalene tetracarboxydiimide (NaPh) central π-conjugated cores with carbon alkyl chains at both sides, grafted on gold through a thiolate. Water contact angles of 100-108° consistent with methyl end-groups on top of the SAM, and infrared and X-ray photoelectron spectroscopy reveal close-packed upright molecules. Scanning tunneling microscopy (STM) shows domains with typical hexagonal ordering [3] for 3T SAMs due to the flexibility given by the alkyl chain, but no NaPh molecular organization could be observed the latter being hindered by the larger NaPh core. Local current-voltage (I-V) characteristics performed under STM tip either on single 3T or NaPh SAMs, or on binary alkylthiol/3T or alkylthiol/NaPh SAMs are shown to correlate well with macroscopic I-V curves measured using eutectic GaIn contacts and to be related with the intrinsic electrical properties of molecules. Contrary to alkylthiol SAMs that exhibit symmetric I-V curve, donor or acceptor type of 3T or NaPh SAMs is revealed by opposite current rectifications. I-V curves were analyzed by Transition Voltage Spectroscopy (TVS) in which the voltage VT at the minimum of the Fowler-Nordheim plot ($\ln(I/V^2)$ vs $1/V$) is proportional to the energy barrier [4]. For alkylthiol SAMs we found V_T~1.1-1.4V, close to that reported by Beebe et al. [4]. HOMO and LUMO positions of the SAMs were extracted using UV photoelectron (UPS) and inverse photoemission spectroscopy (IPES) respectively. From measured values, we show that V_T obtained for the various molecules (0.5-1.1V) corresponds with the bias necessary to reach the tail of the HOMO or LUMO density of states closest to the Fermi level, as proposed in the literature [5]. At last, most importantly we show from the SAMs of the various studied molecules that the better structured the SAMs the narrower the distribution of their transition voltage V_T obtained by TVS, thus giving evidence of a relationship between structural and electrical properties.

We acknowledge support from ANR-11-BS10-012 (SAGe III-V project) and SCS competitive cluster.

References

[1] R.L. Carroll, C.B. Gorman, Angew.Chem.Int.Ed. 41 (2002) 4378.
[2] D. Guérin et al., J.Mat.Chem. 20 (2010) 2680.
[3] A. Ulman, An introduction to ultrathin organic films, (Academic Press, Boston, 1991).
[4] I. Bâldea, Phys.Rev.B,85, 035442 (2012); J.M. Beebe et al., ACS Nano, 2 (2008) 827.
[5] M. Araidai, M. Tsukada, Phys.Rev.B, 81 (2010) 235114.




Figure 1. STM I(V) of NaPh & 3T SAMs on Au(111). Bias is applied to the sample. Inset shows TVS graph: the bias V_T at the minimum corresponds to the energy barrier and correlates with HOMO and LUMO onset measured by UPS and IPES respectively.