



HAL
open science

In situ analysis of the protein corona by
cryo-transmission electron microscopy

Jéril Degrouard, Laurent Marichal, Stéphanie Devineau, Gaël Giraudon-
Colas, Yves Boulard, Jean-Philippe Renault, Serge Pin

► **To cite this version:**

Jéril Degrouard, Laurent Marichal, Stéphanie Devineau, Gaël Giraudon- Colas, Yves Boulard, et al..
In situ analysis of the protein corona by cryo-transmission electron microscopy. 17ème Colloque de
la Société Française des Microscopies, Jul 2021, Reims (E-Conference), France. . cea-03356100

HAL Id: cea-03356100

<https://hal-cea.archives-ouvertes.fr/cea-03356100>

Submitted on 27 Sep 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

IN SITU ANALYSIS OF THE PROTEIN CORONA BY CRYO-TRANSMISSION ELECTRON MICROSCOPY

Jéril DEGROUARD^{1,*}, Laurent MARICHAL¹, Stéphanie DEVINEAU², Gaël GIRAUDON-COLAS⁴, Yves BOULARD³, Jean-Philippe RENAULT⁴, Serge PIN⁴

¹ Université Paris-Saclay, CNRS, UMR 8502, Laboratoire de Physique des Solides, 91405 Orsay Cedex, France

² Université de Paris, BFA, UMR 8251, CNRS, F-75013 Paris, France

³ Université Paris-Saclay, CEA, CNRS, I2BC, B3S, Gif-sur-Yvette 91190, France

⁴ Université Paris-Saclay, CEA, CNRS, NIMBE, Gif-sur-Yvette 91190, France

In a biological environment, the adsorption of proteins on nanoparticles (NPs) is an early process that leads to major changes of the physicochemical properties and the biological effects of NPs. The formation of the so-called protein corona drives NP-cell interaction, NP biodistribution, and NP toxicity *in vivo*. However, few experimental techniques allow for the analysis of the protein corona *in situ*. As a result, little is known on its structure.


Using silica NPs and a library of purified hemoproteins with sizes ranging from 2.8 to 22 nm in diameter (17 to 3,600 kDa in MW), we investigated the effect of protein size on the protein corona assembly by cryo-TEM. Our observations revealed that larger proteins, composed of more than a hundred subunits, form open networks with NPs rather than a homogeneous monolayer of proteins decorating the surface as observed for smaller ones (Figure 1) [1]. The ability of each protein to bind to several NPs drives the formation of novel supramolecular assemblies, while preserving protein structure and function, here in terms of oxygenation properties. By combining cryo-TEM and synchrotron radiation circular dichroism, we further showed that NPs can stabilize partially unfolded protein conformations, thereby driving the formation of a 'soft protein corona' consisting of small weakly bound proteins directly adsorbed to the surface, a dynamic process associated with the partial loss of protein structure and stability (Figure 2) [2]. These results highlight the need for *in situ* analytical approaches to investigate the structuring and driving forces of protein adsorption on nanomaterials to better our understanding of their effects in biologically relevant conditions.

Acknowledgements: Cryo-TEM experiments were supported by the METSA network (Proposal FR3507) and by the French Investissements d'Avenir LabEx PALM (ANR-10LABX-0039- PALM).

References :

[1] From Protein Corona to Colloidal Self-Assembly: The Importance of Protein Size in Protein-Nanoparticle Interactions. Marichal L. *et al.* Langmuir (2020) 36, 8218-8230.

[2] *In situ* analysis of weakly bound proteins reveals molecular basis of soft corona formation. Sanchez-Guzman D. *et al.* ACS Nano (2020) 14, 9073-9088.



*Figure 1: Cryo-TEM image of *Arenicola marina* hemoglobin (22 nm in diameter) interacting with silica nanoparticles in phosphate buffer (100 mM, pH 6). The corresponding schematic highlights the orientation of the proteins (in purple) relative to the NPs (in black). Scale bar 30 nm. From [1]*




Figure 2: Analysis of the soft protein corona formed by human hemoglobin (oxyHb) on silica nanoparticles (SNPs) by cryoTEM. Automated image analysis was performed to identify proteins adsorbed on silica nanoparticles (in red and in blue respectively). Scale bar is 20 nm. From [2]

* jeril.degrouard@universite-paris-saclay.fr