

Glass-Iron-Claystone interactions: a study relying on characterizations and geochemical modeling

Alexis Delanoë, Charly Carrière, Philippe Dillmann, Delphine D. Neff, C. Martin, Olivier Bildstein, Jean-Eric Lartigue, S. Gin

▶ **To cite this version:**

Alexis Delanoë, Charly Carrière, Philippe Dillmann, Delphine D. Neff, C. Martin, et al.. Glass-Iron-Claystone interactions: a study relying on characterizations and geochemical modeling. 8th International Workshop on Long-term Prediction of Corrosion in Nuclear Waste Systems, Jun 2022, Baden, Switzerland. cea-03703755

HAL Id: cea-03703755
https://cea.hal.science/cea-03703755

Submitted on 24 Jun 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Abstract LTC 2022

Glass-Iron-Claystone interactions: a study relying on characterizations and modeling

500 words

Carbon steel containers session

1 img 60*800 pixel jpg png

In France, Andra considers to dispose High-level waste in deep geological repository. The concept rely on disposal cells dug into the Callovo-Oxfordian claystone, where stainless steel canisters filled up with vitrified borosilicate glass would be disposed. Understanding the waste forms degradation in contact with groundwater is crucial to assess the release of radionuclides in the geosphere. Canisters corrosion would release iron into the groundwater, and therefore the Fe-containing solution would alters the glass.

The purpose of this work is to investigate the glass-iron-claystone interactions in conditions close to that expected in a geological repository. A mockup experiment composed of two SON68 glass coupons (one of them doped with ^{57}Fe and ^{29}Si) in contact with an iron piece surrounded by a Callovo-Oxfordian claystone cylinder was setup. The claystone was saturated with synthetic groundwater, under anoxic atmosphere. Two identical mockups were prepared and run in parallel at 50°C for 2.5 [1] and 6.1 years, respectively.

Post-mortem multi-scale characterizations were performed on the samples. They rely on SEM, EDS, Raman spectroscopy, LA-ICP-MS, Tof-SIMS, HRTEM, and STXM to identify the phases, investigate the corrosion products and alteration layers, and discuss the underlying mechanisms.

The release of Fe and Si into the groundwater lead to the formation of iron phyllosilicates into the glass alteration layer and iron corrosion products. Their precipitation on the glass surface prevents the formation of an amorphous silica passivating layer, keeping high glass alteration rates (around $r_0/4$, where r_0 represents the initial dissolution rate of the glass) which is far from the residual rate ($r_0/1550$). Interestingly, two types of phyllosilicates were characterized in the iron corrosion products and the glass alteration layer: 10.4Å-phyllosilicates and 7.8Å-phyllosilicates, after 2.5 and 6.1 years respectively. These results suggest an evolution of the system between the two mockup. Aqueous parameters (pH, [Si], [Fe], …) might play a relevant role on phyllosilicates formation, glass alteration and iron corrosion. A modeling approach is under developement using Hytec and Crunch reactive transport codes to reproduce the phenomena observed and the geochemical evolution of the mockup.

[1] C. Carrière and al. *NPJ Materials Degradation, 5,* **2021** (The fate of Si and Fe while nuclear glass alters with steel and clay)